



IEEE Standard for Pad-Mounted Equipment—Enclosure Integrity for Coastal Environments

IEEE Power Engineering Society

Sponsored by the
Transformers Committee

C57.12.29TM

IEEE
3 Park Avenue
New York, NY 10016-5997, USA

10 November 2005

IEEE Std C57.12.29™-2005

IEEE Standard for Pad-Mounted Equipment—Enclosure Integrity for Coastal Environments

Sponsor

Transformers Committee
of the
IEEE Power Engineering Society

Approved 10 May 2005

IEEE-SA Standards Board

Abstract: Covered in this standard are conformance tests and requirements for the integrity of above-grade pad-mounted enclosures for application in coastal environments that contain apparatus energized in excess of 600 V and that may be exposed to the public including, but not limited to, the following types of equipment enclosures: pad-mounted capacitors or inductors, pad-mounted distribution transformers, pad-mounted junction enclosures, pad-mounted metering equipment, pad-mounted switch gear.

Keywords: enclosure integrity, pad-mounted equipment, switches, transformers

The Institute of Electrical and Electronics Engineers, Inc.
3 Park Avenue, New York, NY 10016-5997, USA

Copyright © 2005 by the Institute of Electrical and Electronics Engineers, Inc.
All rights reserved. Published 10 November 2005. Printed in the United States of America.

IEEE is a registered trademark in the U.S. Patent & Trademark Office, owned by the Institute of Electrical and Electronics Engineers, Incorporated.

National Electrical Safety Code and NESC are registered trademarks and service marks of the Institute of Electrical and Electronics Engineers, Inc.

Print: ISBN 0-7381-4713-3 SH95341
PDF: ISBN 0-7381-4714-1 SS95341

No part of this publication may be reproduced in any form, in an electronic retrieval system or otherwise, without the prior written permission of the publisher.

IEEE Standards documents are developed within the IEEE Societies and the Standards Coordinating Committees of the IEEE Standards Association (IEEE-SA) Standards Board. The IEEE develops its standards through a consensus development process, approved by the American National Standards Institute, which brings together volunteers representing varied viewpoints and interests to achieve the final product. Volunteers are not necessarily members of the Institute and serve without compensation. While the IEEE administers the process and establishes rules to promote fairness in the consensus development process, the IEEE does not independently evaluate, test, or verify the accuracy of any of the information contained in its standards.

Use of an IEEE Standard is wholly voluntary. The IEEE disclaims liability for any personal injury, property or other damage, of any nature whatsoever, whether special, indirect, consequential, or compensatory, directly or indirectly resulting from the publication, use of, or reliance upon this, or any other IEEE Standard document.

The IEEE does not warrant or represent the accuracy or content of the material contained herein, and expressly disclaims any express or implied warranty, including any implied warranty of merchantability or fitness for a specific purpose, or that the use of the material contained herein is free from patent infringement. IEEE Standards documents are supplied “**AS IS.**”

The existence of an IEEE Standard does not imply that there are no other ways to produce, test, measure, purchase, market, or provide other goods and services related to the scope of the IEEE Standard. Furthermore, the viewpoint expressed at the time a standard is approved and issued is subject to change brought about through developments in the state of the art and comments received from users of the standard. Every IEEE Standard is subjected to review at least every five years for revision or reaffirmation. When a document is more than five years old and has not been reaffirmed, it is reasonable to conclude that its contents, although still of some value, do not wholly reflect the present state of the art. Users are cautioned to check to determine that they have the latest edition of any IEEE Standard.

In publishing and making this document available, the IEEE is not suggesting or rendering professional or other services for, or on behalf of, any person or entity. Nor is the IEEE undertaking to perform any duty owed by any other person or entity to another. Any person utilizing this, and any other IEEE Standards document, should rely upon the advice of a competent professional in determining the exercise of reasonable care in any given circumstances.

Interpretations: Occasionally questions may arise regarding the meaning of portions of standards as they relate to specific applications. When the need for interpretations is brought to the attention of IEEE, the Institute will initiate action to prepare appropriate responses. Since IEEE Standards represent a consensus of concerned interests, it is important to ensure that any interpretation has also received the concurrence of a balance of interests. For this reason, IEEE and the members of its societies and Standards Coordinating Committees are not able to provide an instant response to interpretation requests except in those cases where the matter has previously received formal consideration. At lectures, symposia, seminars, or educational courses, an individual presenting information on IEEE standards shall make it clear that his or her views should be considered the personal views of that individual rather than the formal position, explanation, or interpretation of the IEEE.

Comments for revision of IEEE Standards are welcome from any interested party, regardless of membership affiliation with IEEE. Suggestions for changes in documents should be in the form of a proposed change of text, together with appropriate supporting comments. Comments on standards and requests for interpretations should be addressed to:

Secretary, IEEE-SA Standards Board
445 Hoes Lane
Piscataway, NJ 08854
USA

NOTE—Attention is called to the possibility that implementation of this standard may require use of subject matter covered by patent rights. By publication of this standard, no position is taken with respect to the existence or validity of any patent rights in connection therewith. The IEEE shall not be responsible for identifying patents for which a license may be required by an IEEE standard or for conducting inquiries into the legal validity or scope of those patents that are brought to its attention.

Authorization to photocopy portions of any individual standard for internal or personal use is granted by the Institute of Electrical and Electronics Engineers, Inc., provided that the appropriate fee is paid to Copyright Clearance Center. To arrange for payment of licensing fee, please contact Copyright Clearance Center, Customer Service, 222 Rosewood Drive, Danvers, MA 01923 USA; +1 978 750 8400. Permission to photocopy portions of any individual standard for educational classroom use can also be obtained through the Copyright Clearance Center.

Introduction

This introduction is not part of IEEE Std C57.12.29-2005, IEEE Standard for Pad-Mounted Equipment—Enclosure Integrity for Coastal Environments.

The Accredited Standards Committee on Transformers, Regulators, and Reactors, C57, has for a number of years been developing and correlating standards on these products. The data used in this work have been gathered from many sources, including the standards of the Institute of Electrical and Electronics Engineers and the National Electrical Manufacturers Association, reports of committees of the Edison Electric Institute, and others.

This IEEE standard is a voluntary consensus standard. Its use becomes mandatory only when required by a duly constituted legal authority or when specified in a contractual relationship. To meet specialized needs and to allow innovation, specific changes are permissible when mutually determined by the user and the producer, provided such changes do not violate existing laws and are considered technically adequate for the function intended.

This standard was originally prepared by the Joint C57/C37 Working Group on Enclosures with J. Martin and then R. C. Olen as chairman. This group is now the Enclosure Integrity Working Group of the IEEE Transformers Committee.

Notice to users

Errata

Errata, if any, for this and all other standards can be accessed at the following URL: <http://standards.ieee.org/reading/ieee/updates/errata/index.html>. Users are encouraged to check this URL for errata periodically.

Interpretations

Current interpretations can be accessed at the following URL: <http://standards.ieee.org/reading/ieee/interp/index.html>.

Patents

Attention is called to the possibility that implementation of this standard may require use of subject matter covered by patent rights. By publication of this standard, no position is taken with respect to the existence or validity of any patent rights in connection therewith. The IEEE shall not be responsible for identifying patents or patent applications for which a license may be required to implement an IEEE standard or for conducting inquiries into the legal validity or scope of those patents that are brought to its attention.

Participants

At the time this standard was completed, the Enclosure Integrity Working Group had the following membership:

Robert Olen, *Chair*
Daniel Mulkey, *Co-Chair*

Glenn Andersen	Ali Ghafourian	Ken Romano
Ignacio Ares	Myron Gruber	Jeff Schneider
Israel Barrientos	Jeremy Guardado	Stephen Shull
Dana Basel	Richard Hollingsworth	Edward Smith
Bikash Basu	Gael R. Kennedy	Steve Snyder
John Borst	Ron Kirker	Ronald Stahara
Paul Buchanan	Brian Klaponski	Giuseppe Termini
Joseph Carulli	Stanley Kostyal	Alan Traut
Tommy Copper	Raymond Loback	Donnie Trivitt
Michael Culhane	Kent Miller	Shelby Walters
Kevin de la Houssaye	Carl Niemann	Dave Weigand
Charlie Drexler	Ernest Nols	Alan Wilks
Philip Fahey	Tim Olson	Michael Williams
	Thomas Pekarek	

The following members of the individual balloting committee voted on this standard. Balloters may have voted for approval, disapproval, or abstention.

David Aho	James Gardner	Paulette Payne
Paul Barnhart	Myron Gruber	Thomas Pekarek
Wallace Binder	Dudley Galloway	Alvaro Portillo
Thomas Blair	Eduardo Garcia	James Ruggieri
David Blew	Ali Ghafourian	Dinesh Sankarakurup
John Borst	Randall Groves	Devki Sharma
Christopher Brooks	Wayne Hansen	Stephen Shull
Carl Bush	Kenneth Hanus	H. Jin Sim
Craig Colopy	Michael Hardin	Chuck Simmons
Roy A. Coquitt, Jr.	Edward Horgan, Jr.	James E. Smith
Tommy Cooper	James D. Huddleston III	James Smith
Jerry Corkran	Gael R. Kennedy	Jerry Smith
Michael Culhane	Stanley Kostyal	Ronald Stahara
R. Daubert	Gregory Luri	John Sullivan
Matthew Davis	William Majeski	John Teixeira
Kevin de la Houssaye	John Matthews	Giuseppe Termini
Guru Dutt Dhingra	Lee Matthews	Alan Traut
Randall Dotson	Frank Mayle	Shelby Walters
Charles Drexler	G. Michel	Tom Wandeloski
Gary Engmann	Dan Mulkey	Dave Wiegand
Jorge Fernandez-Daher	Robert Olen	Alan Wilks
Phillip Fahey	T. W. Olsen	Michael Williams
Marcel Fortin	Tim Olson	Bill Wimmer
	Gerald Paiva	

When the IEEE-SA Standards Board approved this standard on 10 May 2005, it had the following membership:

Don Wright, *Chair*
Steve M. Mills, *Vice Chair*
Judith Gorman, *Secretary*

Chuck Adams
Stephen Berger
Mark D. Bowman
Joseph A. Bruder
Bob Davis
Roberto de Marca Boisson
Julian Forster*
Arnold M. Greenspan
Mark S. Halpin

Raymond Hapeman
Richard J. Holleman
Richard H. Hulett
Lowell G. Johnson
Joseph L. Koepfinger*
Hermann Koch
Thomas J. McGean

Daleep C. Mohla
Paul Nikolich
T. W. Olsen
Ronald C. Petersen
Gary S. Robinson
Frank Stone
Malcolm V. Thaden
Doug Topping
Joe D. Watson

*Member Emeritus

Also included are the following nonvoting IEEE-SA Standards Board liaisons:

Satish K. Aggarwal, *NRC Representative*
Richard DeBlasio, *DOE Representative*
Alan Cookson, *NIST Representative*

Jennie Steinhausen
IEEE Standards Project Editor

Contents

1. Overview	1
1.1 Scope	1
1.2 Purpose	1
2. Normative references.....	1
3. Definitions.....	2
4. Enclosure security	3
4.1 Test requirements	3
4.2 Test equipment	4
4.3 Resistance to foreign objects	5
4.4 Test values	6
5. Enclosure design and coating system requirements	7
5.1 Enclosure design requirements—objective.....	7
5.2 Substrate requirements.....	7
5.3 Coating system requirements.....	8
5.4 Coating system test specimens	8
5.5 Coating system performance requirements.....	8
6. Labels	10
6.1 Purpose	10
6.2 Application	10
7. General	10
7.1 Shipment.....	10
7.2 Coating repair procedure	10
Annex A (normative) Procedure for comparative weight loss	16
Annex B (informative) Pry bar.....	17
B.1 General.....	17
B.2 Drawings.....	17
B.3 Assembly instructions.....	18
Annex C (informative) Bibliography.....	21

IEEE Standard for Pad-Mounted Equipment—Enclosure Integrity for Coastal Environments

1. Overview

1.1 Scope

This standard covers conformance tests and requirements for the integrity of above-grade pad-mounted enclosures intended for installation in coastal environments containing apparatus energized in excess of 600 V that may be exposed to the public including, but not limited to, the following types of equipment enclosures:

- a) Pad-mounted capacitors or inductors
- b) Pad-mounted distribution transformers
- c) Pad-mounted junction enclosures
- d) Pad-mounted metering equipment
- e) Pad-mounted switchgear

This standard does not cover installations that are under the exclusive control of electric utilities and that are located in such a manner that access to the equipment is controlled exclusively by the utility.

1.2 Purpose

The purpose of this standard is to describe the requirements for a comprehensive integrity system for pad-mounted enclosures providing long field life with minimum maintenance and positive safety features.

2. Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments or corrigenda) applies.

ASTM D523, Standard Test Method for Specular Gloss.¹

ASTM D1654-2005, Standard Test Method for Evaluation of Painted or Coated Specimens Subjected to Corrosive Environments.

ASTM D3170, Standard Test Method for Chipping Resistance of Coatings.

ASTM D3359, Standard Test Methods for Measuring Adhesion by Tape Test.

ASTM D3363, Standard Test Method for Film Hardness by Pencil Test.

ASTM D4060, Standard Test Method for Abrasion Resistance of Organic Coatings by the Taber Abraser.

ASTM D4585, Standard Practice for Testing Water Resistance of Coatings Using Controlled Condensation.

ASTM D4587, Standard Practice for Fluorescent UV-Condensation Exposures of Paint and Related Coatings.

SAE J400, Test for Chip Resistance of Surface Coatings.²

3. Definitions

For the purposes of this standard, the following terms and definitions apply. *The Authoritative Dictionary of IEEE Standards* [B10]³ should be referenced for terms not defined in this clause.

3.1 above grade: A term referring to an equipment use location above the high water line not intended for partial or total submersion.

3.2 axial force: A force applied along the axis of the pry bar from its handle to its pry tip.

3.3 coastal environment: The land area within 760 m (2500 ft) of the mean high water line.

3.4 conformance tests: Certain performance tests are conducted to demonstrate compliance with the applicable standards. The test specimen is normally subjected to all planned routine tests prior to initiation of the conformance test program.

NOTE—The conformance tests may, or may not, be similar to certain design tests. Demonstration of margins (capabilities) beyond the standard requirements is unnecessary.⁴

3.5 design tests: Tests made by the manufacturer to determine the adequacy of the design of a particular type or model of equipment or its component parts to meet its assigned ratings and to operate satisfactorily under normal conditions and under special conditions if specified. These tests may be used to demonstrate compliance with applicable standards of the industry.

¹ ASTM publications are available from the American Society for Testing and Materials, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959, USA (<http://www.astm.org/>).

² SAE publications are available from the Society of Automotive Engineers, 400 Commonwealth Drive, Warrendale, PA 15096, USA (<http://www.sae.org/>).

³ The numbers in brackets correspond to those of the bibliography in Annex C.

⁴ Notes in text, tables, and figures of a standard are given for information only, and do not contain requirements needed to implement the standard.

NOTE—Design tests, sometimes called type tests, are made on representative apparatus or prototypes to verify the validity of design analysis and calculation methods and to substantiate the ratings assigned to all other apparatus of basically the same design. These tests may also be used to evaluate the modification of a previous design and to ensure that performance has not been adversely affected. Test data from previous similar designs may be used for current designs, where appropriate. Once made, the tests need not be repeated unless the design is changed so as to modify performance.

3.6 dry film thickness: Thickness of any applied coating(s) measured after curing.

3.7 enclosure security: The completely assembled apparatus will resist unauthorized entry when tested in accordance with the procedures of this standard.

3.8 gel coat: The material that provides the inhibition for ultraviolet protection and color to the fiber reinforced plastic (FRP).

3.9 padlock: A locking device specified by the user that will prevent the disengagement of the pentahead device. (e.g., key or combination lock, one-time or twist lock, single-use lock, or similar device.)

3.10 pad-mounted enclosure: An enclosure containing electrical apparatus, typically located outdoors at ground level where the general public has direct contact with the exterior surfaces of the equipment. The general construction of this equipment shall be such that authorized personnel may obtain access to the apparatus inside the equipment compartment(s).

3.11 prying leverage: A force at right angles to the handle times the distance from this force to the point of insertion of the pry tip into a joint, crevice, or similar opening in enclosure.

3.12 routine tests: Tests made for quality control by the manufacturer on every device or representative samples, or on parts or materials as required to verify during production that the product meets the design specifications and applicable standards.

NOTE 1—Certain quality assurance tests on identified critical parts of repetitive high-production devices may be tested on a planned statistical sampling basis.

NOTE 2—"Routine tests" are sometimes called "production tests."

3.13 substrate: The material that provides structural integrity to the enclosure.

4. Enclosure security

4.1 Test requirements

In addition to passing the tests defined in this standard, the construction of pad-mounted enclosure shall comply with the requirements of 4.1.1 through 4.1.9.

4.1.1 Enclosure mounting

The bottom edge of the enclosure shall provide for flush mounting on a flat, rigid mounting surface.

4.1.2 Water resistance

The enclosure shall restrict the entry of water (other than flood water) into the enclosure so as not to impair the operation of the apparatus inside.

4.1.3 Sharp corners

External sharp corners and projections shall be minimized.

4.1.4 Panel assembly

Panels shall be fastened or hinged to resist disassembly, breaking, or prying open from the outside with the doors in the closed and locked position. Normal entry shall be possible only with the use of proper access tools. There shall be no exposed screws, bolts, or other fastening devices that are externally removable (with the exception of pentahead bolts provided for extra security) that would provide access to energized parts in the enclosure.

4.1.5 Door hardware

Locking bolts and associated threaded receptacles, hinges, and hinge pins shall be AISI-type 304 stainless steel or material of equivalent corrosion resistance.

4.1.6 Handhole covers

If handhole covers are exposed, they shall be secured from the inside of the enclosure.

4.1.7 Locking/latching devices

The latching device(s) shall be designed and constructed of such a material so as to resist breaking or bending. The provision for locking device(s) on the enclosure door(s) shall be designed and located as to comply with the defined tests.

4.1.8 Enclosure access

All access doors shall be fastened with a device that uses a pentahead tool to permit unlatching the door only after the padlock has been removed. This pentahead device or bolt shall be coordinated such that the padlock may not be inserted into hasp until the access door is fully latched and the pentahead device is securely engaged.

Enclosures without latches shall have padlock and pentahead bolt provisions, and shall be coordinated to prevent insertion of a padlock until the access door is fully closed and the pentahead device or bolt is securely engaged. The padlock shall be removed before the pentahead bolt can be disengaged.

A minimum of one pentahead device or bolt and padlocking means shall be provided. The pentahead device or bolt shall be surrounded by a non-rotating guard or shall be recessed such that the pentahead device or bolt can be engaged only by the proper tool. The dimensions of the pentahead bolt and non-rotating recess shall comply with Figure 1. The pentahead device or bolt shall not be readily removable until the padlock has been removed. More than one door may be fastened with a single padlock and pentahead device or bolt.

4.1.9 Fire resistance

The enclosure shall be constructed of fire-resistant material.

4.2 Test equipment

The tests for enclosure security shall be conducted with the equipment in 4.2.1, 4.2.1.1, 4.2.1.2, 4.2.2, 4.2.3, 4.2.4 or equivalent equipment.

4.2.1 Pry bar

The pry bar shall be constructed with the pry tip shown in Figure 2. The pry bar shall be capable of accurately indicating the axial force and prying leverage specified in Table 1.

Table 1—Test values

Test	Value
Inward axial force	222 N (50 lbf)
Prying leverage tests	102 N•m (900 lbf-in)
Pull test	667 N (150 lbf)
Deflection test	445 N (100 lbf)

4.2.1.1 Tool

The axial force and prying leverage indication may be obtained from a variety of readily available or custom made tools. Annex A includes a complete set of detailed drawings for one set of such tools. Other pry bar designs complying with 4.2.1 are acceptable.

4.2.1.2 Measurement

The prying leverage applied can be measured indirectly by measuring the deflection of the pry bar. The indicator is mounted on the pry bar and set to measure the deflection of a certain length of the bar. A calibration can be made that will result in a table or curve showing prying leverage versus reading of the indicator.

4.2.2 Pull tool

The device shown in Figure 3 shall be used in the pull tests.

4.2.3 Push tool

A device that has a 12.7 mm × 12.7 mm (0.5 in × 0.5 in) square face as shown in Figure 4 with associated indicator to measure axial force shall be used to perform the deflection test.

4.2.4 Probe wire

The probing wire shall be bare number 14 AWG soft-drawn solid copper wire 3 m (10 ft) long.

4.3 Resistance to foreign objects

The following tests are to be performed on the enclosure. The enclosure shall resist the entry of foreign objects such as sticks, rods, or wires.

4.3.1 General

The pad-mounted enclosure shall be mounted on a flat surface according to the manufacturer's specification. With the access door(s) closed and locked using a padlock with an 8 mm (5/16 in) diameter shackle, the following sequence of tests shall be performed:

- a) Pry tests
- b) Wire probe tests

- c) Pull tests
- d) Repeat wire probe tests
- e) Deflection tests
- f) Operation test

4.3.2 Pry tests

The pry bar shall be used on all joints, crevices, hinges, locking means, and other objects that exist between the enclosure components, including the enclosure/pad interface. The pry bar shall be permitted to be placed at any angle to the enclosure surface. The tip of the bar shall first be inserted in the opening being tested using the value of axial force specified in Table 1. Then, with that axial force being maintained, the prying force specified in Table 1 applied alternatively first in one direction and then in the opposite direction (i.e., once in each direction). Application of either or both axial and prying force shall be maintained so long as relaxation is occurring. When relaxation ceases, or if no relaxation occurs, the pry bar shall be removed and pry test reapplied at the same location. When relaxation ceases or no relaxation occurs after the second test, the pry bar shall be removed and applied at an untested location.

4.3.3 Pull tests

A pulling force shall be applied to the critical points of all enclosure parts that can be engaged by the pulling hook. A pulling force indicated in Table 1 shall be exerted at any angle to the enclosure surface. This force is to be maintained during any relaxation. When relaxation ceases, or if no relaxation occurs, the pull test shall be terminated. The hook shall then be inserted into any other part in which it can engage, and the test shall be repeated at the new location. All parts that can be engaged by the pull hook shall be tested once.

4.3.4 Wire probe tests

Following the pry tests and pull tests described in 4.3.2 and 4.3.3, an attempt to penetrate the enclosure with the probe wire shall be made. This penetration shall be attempted at all crevices and joints. The wire shall be straight with no prebends and shall be gripped by the tester with bare hands. If the wire enters the joint, the wire shall be continually pushed and bent until either it can no longer be pushed or it has entered the enclosure completely. This test is passed if an inspection determines the probing wire either has not entered the enclosure or, if visible, the probing wire is restricted by a barrier from intrusion into the interior.

4.3.5 Deflection tests

The deflection test shall be applied to all sides and walls of the enclosure. This test is passed if the specific force (see Table 1) applied perpendicularly to the surface of the enclosure does not impair the dielectric, mechanical, or corrosion performance of the equipment.

4.3.6 Operation test

Following all of the above tests, the enclosure shall be easily unlocked and opened and shall be easily closed and locked.

4.4 Test values

The minimum test values for which entry shall be prevented are provided in Table 1.

5. Enclosure design and coating system requirements

5.1 Enclosure design requirements—objective

The objective of this clause is to describe design and performance requirements for pad-mounted enclosures situated in coastal salt-water environments.

5.1.1 Accessibility

The enclosure shall be designed such that all exterior surfaces are accessible for proper surface preparation and the application of a uniform amount of the coating materials. Additionally, all exterior surfaces of the enclosure shall be accessible for the purposes of inspection and maintenance of the enclosure over the life of the equipment.

5.1.2 Contaminant accumulation

The enclosure shall be designed to shed water and minimize areas where corrosive elements can accumulate.

5.1.3 Welds—surface preparation

All welds shall be treated to prepare the weld area and the heat-affected zones for coating. Weld splatter shall be removed. All welds shall be made in accordance with appropriate industrial welding standards.

5.2 Substrate requirements

5.2.1 General

The substrate shall be a material that, when coated or otherwise processed, will maintain the structural integrity of the enclosure over the life of the apparatus.

5.2.2 Specification of substrate characteristics

The apparatus enclosure substrate shall exhibit a general corrosion rate not to exceed 0.03 mm (0.001 in) per year and a maximum pit depth not to exceed 0.13 mm (0.005 in) over the life of the apparatus, when exposed to natural corrosive environments.

5.2.3 Substrate performance requirements

Five substrate test panels and five AISI 409 stainless steel control test panels shall be evaluated for percent weight loss after exposure to 1500 h of salt spray in accordance with ASTM B117.⁵ The average weight loss of each set of test panels shall not exceed 2.5%. In addition, the ratio of the average percent weight loss between the substrate test panel set and the control test panel set shall not exceed 5 to 1.⁶

The AISI 409 stainless steel control test panels shall be unwelded but fabricated and pretreated in accordance with Figure 10 (non-welded substrate test panel) using standard production practices prior to testing. For metallic substrates, the substrate test panels shall be fabricated in accordance with Figure 9 (welded substrate test panel) using standard production, fabrication, welding, and cleaning practices. For

⁵ For information on references, see Clause 2.

⁶ It is not uncommon for a welded test panel to exhibit greater weight loss due to the galvanic action between the weldment and the base metal.

non-metallic substrates, the substrate test panels shall be fabricated in accordance with Figure 10 (non-welded substrate test panel) using standard production, fabrication, and cleaning practices.

See Annex A for the procedure for comparative weight loss analysis of the test panels.

5.3 Coating system requirements

5.3.1 General

All coated or gel-coated surfaces on the exterior or interior of the enclosure that may be exposed to the atmosphere shall be capable of meeting the performance tests required by this standard.

5.3.2 Specification of coating characteristics

If more than one coating system is used for different areas of the enclosure, the areas in which each is used shall be identified. The laboratory test performance data of each coating system shall be identified. The laboratory test performance data of each coating system shall be submitted for approval upon request. This data shall be resubmitted whenever there are changes in the method and/or materials.

5.3.3 Coating touch-up prior to shipment

Touch-up, when required, shall be done at final inspection before any equipment is shipped. In areas where the integrity of the coating system is violated, the touch-up shall blend smoothly and meet all performance criteria of this standard.

5.3.4 Enclosure color

Unless otherwise specified, the topcoat color shall be Munsell Number 7GY 3.29/1.5 pad-mount green. The color variation of the coated product shall not exceed the Munsell Color Standard [B17] by more than a ΔE (Hunter) value of four.

5.4 Coating system test specimens

Test specimens shall consist of panels of the same material composition used in production. Test specimens shall be in accordance with Figure 5, Figure 6, Figure 7, and Figure 8 as to size and type. Quantity and type of panels in each test are identified under the specific test. All panels shall be cleaned, coated, and cured using the production coating system. Coated test panels shall be conditioned at room temperature and humidity for a minimum of 7 d prior to any testing.

5.5 Coating system performance requirements

5.5.1 Exposure test

5.5.1.1 Exposure test site

A marine environment for natural accelerated testing, located on the ocean or Gulf of Mexico, with a view of the surf-line that is unrestricted by buildings. Corrosion rate for an ingot of iron of AISI 1008 carbon steel shall be greater than 254 μm (10 mil) per year as determined by annual evaluation. Monitoring for chloride deposition (monthly), iron ingot corrosion rate (annual), temperature, and rainfall shall be maintained and historical data provided upon request.

NOTE—Examples of test sites that meet these criteria are Battelle Memorial Institute's Florida Materials Research Facility (Daytona Beach, FL) and LaQue Corrosion Service's Marine Atmospheric Test Site (Wrightsville Beach, NC).⁷

5.5.1.2 Exposure test criteria

This test requirement shall apply to the coating systems applied to both the exterior and interior cabinet/frontplate surfaces of the electrical distribution device. Three coated panels, shown in Figure 5 (corrosion coating test panel), shall be scribed per ASTM D1654 and tested for 12 weeks at a test site that meets the criteria in 5.5.1.1. The panels shall be exposed in a rack facing the ocean at a 30° angle from the horizontal and positioned to ensure that moisture runs down the length of the scribe line during the exposure period.

5.5.1.3 Exposure test evaluation

After the 12-week exposure, prepare the scribe for evaluation as given in Procedure A, Method 2 of ASTM D1654-2005. The scribe shall be divided into 14 6.3 mm (0.25 in) zones and the worst spot in each zone will be evaluated (except the first 6.3 mm (0.25 in) of the scribe at each end of the scribe line). The average of the 14 readings shall be rated as given in Table 1 of ASTM D 1654-2005. After a rating has been set for each of the three panels, the average rating of the three panels shall not be less than a 9 rating. The area away from the scribe shall have no blisters and be free of any corrosion bleed-through. The 6.3 mm (0.25 in) area around the perimeter of the panel and hanging hole shall not be included in the rating of the face of the panel.

5.5.2 Crosshatch adhesion test

One coated test panel, shown in Figure 6 (plain coating test panel), shall be scribed to bare metal in accordance with ASTM D3359. Method A shall be used for films thicker than 0.13 mm (5 mil or 0.005 in) and method B shall be used for films less than or equal to 0.13 mm (5 mil or 0.005 in). There shall be 100% adhesion to the substrate and between layers. A rating of 5A for method A and 5B for method B per ASTM D3359 is required.

5.5.3 Humidity test

Two coated panels, shown in Figure 5 (corrosion coating test panel), shall be tested for 1000 h in accordance with ASTM D4585 except that the test shall be conducted at 45 °C ± 1 °C (113 °F ± 2 °F). Upon completion of the test, panels shall be evaluated for the following:

- a) Blistering—There shall be no blistering observed on the surface of the panels when inspected within 15 min after removal from the cabinet.
- b) Softening—After removal from the cabinet, allow the panels to air dry for 24 ± 1 h. There shall be no more than one pencil hardness change when tested per ASTM D3363. Any color change shall be noted.

5.5.4 Insulating fluid resistance tests (for liquid-filled equipment only)

Partially immerse one coated panel, shown in Figure 6 (plain coating test panel), in the insulating liquid for 72 h at 100 °C to 105 °C (212 °F to 221 °F). On the immersed portion of the panel, there shall be no loss of adhesion per ASTM D3359, no blisters, no streaking, and no more than one pencil hardness change per ASTM D3363, using either method. Any color shift shall be noted.

⁷ This information is given for the convenience of users of this standard and does not constitute an endorsement by the IEEE of these test facilities. Equivalent facilities may be used if they can be shown to lead to the same results.

5.5.5 Ultraviolet accelerated weathering test

The following test is required for all coated surfaces on the exterior of the enclosure. Expose two test panels, shown in Figure 6 (plain coating test panel), for 500 h per ASTM D4587, utilizing the FS-40 bulb with a cycle of 4 h ultraviolet at 60 °C (140 °F) followed by 4 h condensation at 50 °C (122 °F). Loss of gloss shall not exceed 50% of original gloss per ASTM D523. The coating shall not exhibit cracking or crazing under unaided visual inspection.

5.5.6 Abrasion resistance Taber Abraser

The following test is required only for coated surfaces on the exterior of the enclosure. One coated panel, shown in Figure 6 (Taber Abraser coating test panel), having the minimum dry film thickness of the total coating system shall be tested using CS-10 wheel, 1000 g weight, in accordance with ASTM D4060. A total number of 3000 cycles shall be run with the wheels resurfaced before testing and after each 500 cycle run. Upon completion of the test, no bare metal shall be present.

5.5.7 Gravelometer

The following test is required only for coated surfaces on the exterior of the enclosure. Two coated panels, shown in Figure 8 (gravelometer coating test panel), are to be tested per ASTM D3170 at room temperature using 414 kPa (60 psig) gauge air pressure. Expose the test panels for 24 h in salt spray per ASTM B117. Remove from salt spray, rinse, and dry panels. Evaluate panels per SAE J400 for quantity and size of rusted chipped areas. Minimum rating shall be 4B per SAE J400.

6. Labels

6.1 Purpose

Labeling can be an important aspect of pad-mounted enclosure integrity. Labeling can alert or inform an individual of potential hazard. Pad-mounted enclosures should be designed to achieve a high degree of integrity. When labels are attached to pad-mounted enclosures, they should be located as close to the hazard as practicable. Labels should be concise and simple to understand, and should accurately communicate the type and degree of hazard.

6.2 Application

The application of any labels, whether intended for interior or exterior use, shall be subject to an agreement between the purchaser and the manufacturer.


7. General

7.1 Shipment

The manufacturer shall provide a method of shipment that will allow the enclosure to be received by the purchaser such that it still meets the performance tests required by this standard.

7.2 Coating repair procedure

A coating system repair procedure shall be recommended by the manufacturer.



NOTE—The captive method is not shown.

Figure 1—Captive and recessed pentahead bolts




Figure 2—Pry bar tip




Figure 3—Pull hook




Figure 4—Pushing tool




Figure 5—Corrosion coating test panel




Figure 6—Plain coating test panel




Figure 7—Taber Abraser coating test panel

NOTE 1—Hole can be placed in panel for hanging for coating operations if required. Locate centered on short dimension and 3.2 mm (1/8 in) to edge of hole on long dimension. Recommended maximum hole size 14.3 mm (9/16 in) in diameter.

NOTE 2—Weld bead to be the same type metal composition as the panel. Weld bead to be 6.4 mm (1/4 in) wide and 3.2 mm (1/8 in) high.

NOTE 3—Hole can be placed in panel for hanging. To be located in one corner. Recommended maximum hole size 14.3 mm (9/16 in) in diameter.

NOTE 4—Scribe per ASTM D1654 across weld approximately 101.6 mm (4 in) scribe length.

NOTE 5—Test panels shall be made from typical production stock of the same material type and thickness used in the construction of the device for which the specified test is intended

NOTE 6—6.4 mm (1/4 in) diameter hole may require reaming to fit Taber Abraser post.




Figure 8—Gravelometer coating test panel

NOTE 1—Hole can be placed in panel for hanging for coating operations if required. Locate centered on short dimension and 3.2 mm (1/8 in) to edge of hole on long dimension. Recommended maximum hole size is 14.3 mm (9/16 in) in diameter.

NOTE 2—Panel thickness to be of typical production stock used in the manufacture of devices test is intended for.




Figure 9—Welded substrate test panel




Figure 10—Non-welded substrate test panel

NOTE 1—Panel thickness to be of typical production stock used in the manufacture of devices for which the test is intended.

NOTE 2—Weld bead to be the same type metal composition as the panel. Weld bead to be 6.4 mm (1/4 in) wide and 3.2 mm (1/8 in) high.

NOTE 3—Hole can be placed in panel if required for processing. Locate centered on short dimension and 3.2 mm (1/8 in) to edge of hole on long dimension. Recommended maximum hole size is 14.3 mm (9/16 in) in diameter.

NOTE 4—Panel is to be cleaned and uncoated.

Annex A

(normative)

Procedure for comparative weight loss

- a) Inspect welded panels to assure that welds are smooth and will not collect salt in any area when exposed in accordance with ASTM B117 with the major axis of the weld upright.
- b) Ensure that all test panels are thoroughly dry. Record the weight of each panel to the nearest 0.0001 g.
- c) Expose all test panels to 1500 h salt spray in accordance with ASTM B117.
- d) After exposure, immediately remove the test specimen and immerse in warm water.
- e) Manually scour each panel while wet using a non-metallic, abrasive pad. Remove rust from pits with a sharp tool.
- f) After scouring all panels, rinse in clean warm water (never let the panels dry until rinsing is complete).
- g) Ensure the test panels are thoroughly dry.
- h) Reweigh the panels to the nearest 0.0001 g and calculate the percent weight loss.

Annex B

(informative)

Pry bar

B.1 General

The pry bar (see Figure B.1) depicted in this informative annex is just one design intended to meet the functional requirements of 4.2.1. Other pry bar designs complying with 4.2.1 are acceptable.

The pry bar consists of three parts: pry tip, torque wrench, and axial force plunger. The pry tip (see Figure B.2) is designed for installation on a 1/2 in drive of a torque wrench. The plunger is designed to be inserted into the handle of a torque wrench with a hollow handle that has an interior stop for the plunger to fit into and press against.⁸

The addition of a pry tip to the torque wrench increases the moment arm of the tool. Consequently, the tool must be recalibrated to account for the longer moment arm. Calibration is accomplished as follows:

- Clamp approximately 1 in of the pry tip to a workbench or other rigid surface.
- Select a point on the torque tool handle to apply force.
- Measure the distance (in inches) from this point to the end of the pry tip.
- Divide 900 in-lb by this distance to determine the force (in pounds) to be applied during calibration.
- Using a calibrated force measurement tool, apply the calculated force to the handle and record the torque indicated on the torque wrench dial.
- This value becomes the target prying leverage force to be used during the pry test.

The plunger is a simple spring force measurement tool made from machined steel parts. The plunger must be calibrated and marked to indicate when the desired force has been reached. The plunger fits into the hollow pipe handle of the torque wrench and must be installed into the torque wrench prior to calibration. Calibration is accomplished as follows:

- Apply force to the plunger using a calibrated force measurement tool.
- As force is applied, the plunger body moves into the torque wrench handle. When the desired force is obtained (50 lb) mark the plunger body at the torque wrench handle rim.
- During the pry test, depress the plunger until the mark aligns with the wrench handle rim.

B.2 Drawings

All dimensions are in inches. All tolerances are ± 0.03 unless otherwise stated.

⁸ At the time of publication of this standard, the Snap-On[®] Model TE100 torque wrench was an example of this technology. This information is given for the convenience of users of this standard and does not constitute an endorsement by the IEEE of this product. Equivalent technology may be used if it can be shown to lead to the same results.

B.3 Assembly instructions

- Insert plunger tip (Figure B.5) from threaded end of plunger sleeve (Figure B.6).
- Insert plunger spring (Figure B.3) from threaded end of plunger sleeve.
- Screw plunger handle (Figure B.4) into plunger sleeve.




Figure B.1—Assembled pry bar




Figure B.2—Pry tip






Figure B.3—Plunger spring



**Material: 1.50 in. Diameter AISI 304
Stainless steel Rod, Annealed
0.825 in. Long**

Figure B.4—Plunger handle



**Material: 11/16 in. Dia. AISI 304 Stainless Steel Rod
Annealed and Ground — 1.900 in. long**

Figure B.5—Plunger tip




Figure B.6—Plunger sleeve




Figure B.7—Plunger assembly

Annex C

(informative)

Bibliography

The following standards are listed here for information only and are not essential for the completion of the requirements of this standard. When the following standards are superseded by an approved revision, the revision shall apply.

- [B1] Accredited Standards Committee C-2, National Electrical Safety Code® (NESC®).⁹
- [B2] ANSI/IEEE C57.12.20™, American National Standard for Overhead Distribution Transformer, 500 kV and Smaller; High-Voltage, 34 500 V and Below, Low Voltage 7970/3800 Y V and Below—Requirements.¹⁰
- [B3] ANSI/IEEE C57.12.21™, American National Standard Requirements for Pad-Mounted, Compartmental-Type Self-Cooled, Single-Phase Distribution Transformers With High Voltage Bushings; High-Voltage, 34 500 GryD/19 920 Volts and Below; Low-Voltage, 240/120 Volts; 167 kVA and Smaller.
- [B4] ANSI/IEEE C57.12.22™, American National Standard for Transformers—Pad-Mounted, Compartmental-Type, Self-Cooled, Three-Phase Distribution Transformers with High-Voltage Bushings, 2500 kVA and Smaller; High-Voltage, 34 500 GrdY/19 920 V and Below; Low Voltage, 480 V and Below—Requirements.
- [B5] ANSI/IEEE C57.12.24™, American National Standard for Transformers—Underground-Type, Three-Phase Distribution Transformers, 2500 kVA and Smaller; High Voltage, 34 500 GrdY/19 920 Volts and Below; Low Voltage, 480 Volts and Below—Requirements.
- [B6] ANSI/IEEE C57.12.25™, American National Standard for Transformers—Pad-Mounted, Compartmental-Type, Self-Cooled, Single-Phase Distribution Transformers with Separable Insulated High-Voltage Connectors; High Voltage, 34 500 GrdY/19 920 Volts and Below; Low Voltage, 240/120 V; 167 kVA and Smaller—Requirements.
- [B7] ANSI/IEEE C57.12.28™, American National Standard—Pad-Mounted Equipment-Enclosure Integrity.
- [B8] ASTM D 714, Standard Test Method of Evaluating Degree of Blistering of Paints.¹¹
- [B9] Bringas, J. E. and Wayman, M. L., *The Metals Black Book, Ferrous Metals*, 3rd ed. Edmonton, AB: CASTI Publishing Inc., 1998.
- [B10] IEEE 100™, *The Authoritative Dictionary of IEEE Standards Terms*, Seventh Edition.¹²

⁹ This publication is available from the Institute of Electrical and Electronics Engineers, 445 Hoes Lane, P.O. Box 1331, Piscataway, NJ 08855-1331, USA.

¹⁰ ANSI/IEEE publications are available from the Institute of Electrical and Electronics Engineers, 445 Hoes Lane, P.O. Box 1331, Piscataway, NJ 08855-1331, USA.

¹¹ ASTM publications are available from the American Society for Testing and Materials, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959, USA (<http://www.astm.org/>).

¹² IEEE publications are available from the Institute of Electrical and Electronics Engineers, 445 Hoes Lane, P.O. Box 1331, Piscataway, NJ 08855-1331, USA (<http://standards.ieee.org/>).

[B11] IEEE Std C57.12.23™, IEEE Standard for Underground-Type, Self-Cooled, Single-Phase, Distribution Transformers with Separable Insulated High-Voltage Connectors; High Voltage 25 000 V and Below; Low-Voltage 600 V and Below; 167 kVA and Smaller.

[B12] IEEE Std C57.12.26™, IEEE Standard for Pad-Mounted, Compartmental-Type, Self-Cooled, Three-Phase Distribution Transformers for Use with Separable Insulated High-Voltage Connectors (34 500 GrdY/19 920 Volts and Below, 2 500 kVA and Smaller).

[B13] IEEE Std C57.12.31™, IEEE Standard for Pole-Mounted Equipment—Enclosure Integrity.

[B14] IEEE Std C57.12.32™, IEEE Standard for Submersible Equipment—Enclosure Integrity.

[B15] IEEE Std C57.12.34™, IEEE Standard Requirements for Pad-Mounted, Compartmental-Type, Self-Cooled, Three-Phase Distribution Transformers, 2500 kVA and Smaller—High-Voltage: 34 500 GrdY/19 920 Volts and Below; Low Voltage: 480 Volts and Below.

[B16] IEEE Std C57.12.35™, IEEE Standard for Bar Coding for Distribution Transformers.

[B17] Munsell Color Standards, Gretag Macbeth Inc., 617 Little Britain Road, New Windsor, NY 12553-6148, USA.

